



DuPont de Nemours, Inc.
SALES SPECIFICATION

Date Printed: 2021-02-01

Effective Date: 2021-01-29

Supersedes Date:

Name: TEXTURECEL™ 30000 P BA Sodium Carboxymethylcellulose

Specification Number: 000001107739

Final Testing Requirements

Test and Test Condition	Limit	Unit	Method	Note
Active Content, dry basis Test Frequency:	99.50 Min audit basis	%	CE-55.4	
Substitution, degree of	0.82 — 0.95		CE-28.4	
Moisture Content, as packaged	5.0 — 8.0	%	CE-7.1	
Sodium Chloride, content	0.40 Max	%	CE-15.5	
pH Value, 1% aqueous solution	6.5 — 8.5		CE-8.1	
Heavy Metals Test Frequency:	10 Max audit basis	ppm	CE-93.1	
Viscosity, Brookfield, LVT, SP.4, 30 rpm, 1% aqueous sol. (dry basis), 25degC	3000 — 4000	mPa.s	CE-5.15	

READ PRECAUTIONARY INFORMATION AND MATERIAL SAFETY SHEETS. THIS PRODUCT IS SHIPPED IN COMPLIANCE WITH APPLICABLE LAWS AND REGULATIONS REGARDING CLASSIFICATION, PACKAGING, SHIPPING AND LABELING.

LAST PAGE